

## Product Information

Internet:  
www.siridion.com  
E-mail:  
siridion@evonik.com

Evonik Degussa GmbH  
Aerosil & Silanes

Weissfrauenstraße 9  
D-60287 Frankfurt am Main  
Germany

Phone: +49-69-218-5656  
Fax: +49-69-218-3496

Evonik Degussa Corporation  
Aerosil & Silanes  
379 Interpace Parkway  
P.O. Box 677  
Parsippany  
NJ 07054-0677  
USA

Phone:  
800-828-8772 (Toll Free)  
+1-973-541-8513  
Fax: +1-973-541-8501

Evonik Degussa (China) Co.,  
Ltd.  
Aerosil & Silanes  
55, Chundong Road  
Xinzhuan Industry Park  
Shanghai 201108  
P.R. China


Phone: +86-21-6119-1052  
Fax: +86-21-6119-1075


  
Siridion®

## Siridion® DCS

### Dichlorosilane, DCS

### Chemical Formula



### Description

Dichlorosilane ( $\text{SiH}_2\text{Cl}_2$ ) is prepared from trichlorosilane by disproportionation.

### Technical data

Property	Value	Unit	Method
molecular weight	101.01	-	
density (7 C°)	1.22	g/cm <sup>3</sup>	DIN 51757
purity	min. 99.0	%	GC (Degussa)
boiling point (1 bar)	8.3 (47)	°C (°F)	DIN 51751
melting point	-122 (-188)	°C (°F)	
flash point	-37 (-34.6)	°C (°F)	DIN 51755
appearance	clear, colourless liquid	-	-
The values given in this Product Information are intended to describe the product.			Decisive documents are agreed specifications and the Material Safety Data Sheet (MSDS).

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

® = registered trademark

## Product Information

Internet:  
www.siridion.com  
E-mail:  
siridion@evonik.com

Evonik Degussa GmbH  
Aerosil & Silanes

Weissfrauenstraße 9  
D-60287 Frankfurt am Main  
Germany

Phone: +49-69-218-5656  
Fax: +49-69-218-3496

Evonik Degussa Corporation  
Aerosil & Silanes  
379 Interpace Parkway  
P.O. Box 677  
Parsippany  
NJ 07054-0677  
USA

Phone:  
800-828-8772 (Toll Free)  
+1-973-541-8513  
Fax: +1-973-541-8501

Evonik Degussa (China) Co.,  
Ltd.  
Aerosil & Silanes  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China

Phone: +86-21-6119-1052  
Fax: +86-21-6119-1075



## Reactivity

Dichlorosilane is sensitive to hydrolysis. It must be stored and transported in closed containers excluding of moisture and air. Protection from direct sunlight and heat is necessary.

Dichlorosilane is highly flammable. Mixtures of DCS vapours with air are explosive and can ignite spontaneously under certain conditions.

The containers must be closed tightly after each time that material is taken out. Owing to the high flammability of dichlorosilane, handling has to be carried out under a blanket of inert gas.

Dichlorosilane (e.g. nitrogen) and its vapours decompose on contact with moisture to form  $\text{SiO}_2$  gel and hydrochloric acid. They react vigorously with water or aqueous solutions and with alcohols or compounds containing active hydrogen atoms.

Dichlorosilane is classified as highly corrosive. Inhaling of the products must be avoided. When handling the product, skin and eyes must be protected by the wearing of impermeable gloves, eye protection and, if appropriate, a breathing mask. Should product nevertheless get onto the skin or into the eyes, the affected area must first be rinsed with plenty of water and, if contact with the eyes has occurred, an eye specialist should be consulted.

## Applications

Dichlorosilane is used for the deposition of epitaxial silicon layers on silicon wafers in semiconductor manufacturing.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

® = registered trademark

## Product Information

Internet:  
www.siridion.com  
E-mail:  
siridion@evonik.com

Evonik Degussa GmbH  
Aerosil & Silanes

Weissfrauenstraße 9  
D-60287 Frankfurt am Main  
Germany

Phone: +49-69-218-5656  
Fax: +49-69-218-3496

Evonik Degussa Corporation  
Aerosil & Silanes  
379 Interpace Parkway  
P.O. Box 677  
Parsippany  
NJ 07054-0677  
USA

Phone:  
800-828-8772 (Toll Free)  
+1-973-541-8513  
Fax: +1-973-541-8501

Evonik Degussa (China) Co.,  
Ltd.  
Aerosil & Silanes  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China

Phone: +86-21-6119-1052  
Fax: +86-21-6119-1075



## Registration

EINECS/ELINCS (EU):	Yes
AICS (Australia):	Yes
DSL (Canada):	Yes
PICCS (Philippines):	Yes
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes

## Safety and Handling

Before considering the use of any chemical thoroughly read its Material Safety Data Sheet (MSDS) for safety and toxicological data as well as for information on proper transportation, storage and use. The Material Safety Data Sheet is available after registration on our website <http://www.siridion.com> or upon request from your local representative.

### Dichlorosilane:

Hazard symbol: F+ = highly flammable; C = corrosive  
(Safety phrases: 3/7/9-16-26-36/37/39-45)

Keep container tightly closed and dry. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. In case of fire, never use water.

Information on the classification of the product under dangerous goods regulations and the German regulation on dangerous substances, safety data and data on toxicology and storage may be found in our Material Safety Data Sheets (MSDS).

## Packaging and Storage

Pressurized stainless steel bottles, contents 9 and 45 kg. Alternative container sizes are available on request.

Siridion® DCS-EN-2008-12

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

® = registered trademark