

# Siridion® GTC

## Germanium tetrachloride, GTC

### Technical data

Properties and test methods	Value	Unit	Method
synonyms	Germanium (IV) Chloride; GeCl <sub>4</sub>	-	-
purity	> 99.999	%	-
formula weight	214.45	-	-
boiling point	83	°C	DIN 51751
theoretical Germanium content	33.873	%	-
specific gravity (20°C)	1.875 g	g/cm <sup>3</sup>	-
Vapor Pressure (20°C)	76mm Hg	-	-
appearance	clear, colorless fuming liquid	-	-

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices.

### Description

Germanium tetrachloride (GeCl<sub>4</sub>) is a colorless liquid. It is used as an intermediate in the production of purified germanium dioxide and germanium metal, but more predominantly used as a reagent in fiber optic production.

### Chemical formula

GeCl<sub>4</sub>

### Reactivity

Germanium tetrachloride is sensitive to hydrolysis and must be stored and transported in closed containers excluding moisture and air. Protection from direct sunlight and heat is necessary.

The containers must be closed tightly after each time that material is taken out.

Germanium chloride and their vapours decompose in presence moisture to form hydrochloric acid. It reacts vigorously with water or aqueous solutions and with alcohols or compounds containing active hydrogen atoms.

GTC is classified as highly corrosive. Inhalation of the product must be avoided. When handling the products, skin and eyes must be protected by the wearing of impermeable gloves, eye protection and, if appropriate, a breathing mask. Should splashes nevertheless get onto the skin or into the eyes, the affected area must first be rinsed with plenty of water and, if contact with the eyes has occurred, an eye specialist should be consulted.

### Applications

In fiber optics, germanium tetrachloride is converted into germanium dioxide and then deposited, along with silicon dioxide, using vapor deposition techniques. Germanium dioxide provides a higher refractive index fiber core, which prevents signal loss during transmission.

## Safety and handling

Before considering the use of any chemical thoroughly read its Safety Data Sheet (SDS) for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.siridion.com](http://www.siridion.com) or upon request from your local representative.

Germanium tetrachloride:  
Hazard symbol: toxic, corrosive  
(Hazard statements: H335/H314, EUH014)

Keep container tightly closed and dry. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

Information on the classification of the products under dangerous goods regulations and the German regulation on dangerous substances, safety data, detailed precautionary statements and data on toxicology and storage may be found in our safety data sheets (SDS).

## Packaging and storage

Stainless steel container with Swagelok valve manifold arrangement with manual operation. Other packaging and valve manifold options available on request. Material is shipped in packaging compliant with the United Nations/Department of Transportation (UN/DOT), the International Air Transportation Association (IATA), and the International Maritime Dangerous Goods (IMDG) code.

Keep the container tightly closed in a dry, cool, and ventilated area. Avoid contact with water. In the originally closed container Siridion® GTC has a shelf life of at least 12 months after delivery.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

### Europe / Middle East / Africa / Latin America

#### Evonik Resource Efficiency GmbH

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13915  
FAX +49 6181 59 713915  
[siridion@evonik.com](mailto:siridion@evonik.com)  
[www.siridion.com](http://www.siridion.com)

### North Amerika

#### Evonik Corporation

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054  
USA  
PHONE +1 973 541 8513  
FAX +1 973 541 8503  
[siridion@evonik.com](mailto:siridion@evonik.com)  
[www.siridion.com](http://www.siridion.com)

### Asia-Pacific

#### Evonik Specialty Chemicals (Shanghai) Co., Ltd

Business Line Silanes  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191 3687  
FAX +86 21 61191 1648  
[siridion@evonik.com](mailto:siridion@evonik.com)  
[www.siridion.com](http://www.siridion.com)